

# STERLING C10 MULTIPURPOSE SPRAY

Sterling C10 Aerosol Contact Adhesive Sterling C10 is an aerosol contact adhesive which does not contain CFC's, it bonds a wide variety of materials giving rapid bond formation and is economical in use. CFC free? Fast Tack? Foaming formula for low soak in? Economical in use Sterling C10 bonds a wide variety of substrates including wood, concrete, stone, tiles, rubber, foam, metals, rigid plastics, polyethylene, canvas fabrics, cardboard, paper and cork. Sterling C10 is ideal for fixing polyethylene sheeting for enclosures prior to asbestos removal, for fixing thermal insulation and for packaging applications such as palletising or case sealing. It may be used for foam bonding, upholstery, automotive, carpets and trim and is useful for temporary bonding instead of double sided tapes. Not suitable for use with plasticised PVC or expanded polystyrene.

**TECHNICAL DATA:** Type: Aerosol

Adhesive Colour: Straw Base: Synthetic Rubber/Resin Application Method: Aerosol Spray Application Temp: +5°C to +40°C Drying Time: 2-5 minutes Clean Up: Solvent Cleaner or white spirit Storage Life: 12 months when stored between 5°C and 25°C in original unopened containers. Packaging: 500ml aerosol cans

**APPLICATION:**

Shake before use. Spray adhesive from 6"–8" away onto one or both surfaces. Surfaces should be clean, dry and free from grease. For one-way application let adhesive dry for 30 seconds until tacky, then press into position. For two-way application, spray both surfaces and allow to dry for 2–5 minutes before bonding. For temporary bonding, spray one surface and allow to dry for 2–5 minutes before bonding. Excess adhesive can be removed with a solvent cleaner or white spirit. To prevent spray nozzle from blocking, at the end of each period of use, turn the can upside down and press nozzle until spray is clear of adhesive.

**HEALTH AND SAFETY DATA:**

Full material safety data sheets are available on request. **IMPORTANT NOTE:** All the information in this data sheet is based on practical experience and is published in good faith. However, because we have no control over the manner or conditions in which our products are used, or over work undertaken or end product manufactured by the purchaser, we cannot accept liability for results. Responsibility for ascertaining the suitability of products for his purposes rests with the purchaser. All conditions, representations, statements, warranties or guarantees whatsoever, whether express, implied or statutory, in respect of any goods manufactured, sold or supplied by us are hereby expressly excluded and we accept no liability in respect of any claim for damage or consequential loss caused to any property arising directly or indirectly out of the use of our products or goods.

